

Quality: A2

Cast quartz with clay bond

Optical	Color	ivory
----------------	-------	-------

Chemical	SiO ₂	71 %
	Clay	13 %
	SiC	11 %
	Rest are trace elements	

Thermal expansion	approx. 0,06 % (1000 °C)
--------------------------	--------------------------

Porosity	< 16 %
-----------------	--------

Thermal shock resistance	gut
---------------------------------	-----

Maximum working temperature	1200 °C (continuous load), 1700 °C (short-term, approx. 10 min.)
------------------------------------	--

All data given are to be regarded as guide values!