

Quality: KR-89-VG

Vibration-cast aluminium oxide

Firing support

Optical	Color	white
Chemical	Al ₂ O ₃ SiO ₂ Rest are trace elements	89 % 10 %
Thermal expansion	appox. 0,75 % (1000 °C)	
Porosity	< 15 %	
Thermal shock resistance	Satisfactory	
Maximum working temperature	1750 °C	

All data given are to be regarded as guide values!